

Total No. Pages Faxed (including cover pages): 4

TO: Examiner U Rajguru
FROM: William Hamby
FAX: 703-305-5885
DATE: 31 October 2001
RE: AD-6506 (SN 09/180,943)

FAX RECEIVED

OCT 31 2001

GROUP 1700

FAX RECEIVED

OCT 31 2001

GROUP 1700

OFFICIALMESSAGE:

We enclose the draft Preliminary Amendment as discussed. Please contact me at 302-992-3230 at your early convenience.

Rry. 10/93

DRAFT**PATENT
IN THE UNITED STATES PATENT AND TRADEMARK OFFICE**

In the Application of:

MASAHIRO NOZAKI

CASE NO.: AD 6506 US CONT.

APPLICATION NO.: 09/180,943
(OF PARENT)GROUP ART UNIT: 1711
(OF PARENT)

FILED: NOVEMBER 18, 1998

EXAMINER: U. RAJGURU
(OF PARENT)FOR: AROMATIC POLYAMIDE RESIN
COMPOSITION HAVING EXCELLENT
BALANCE OF TOUGHNESS AND
STIFFNESS**PRELIMINARY AMENDMENT**Assistant Commissioner for Patents
Washington, DC 20231**OFFICIAL**
FAX RECEIVED
OCT 31 2001
GROUP 1700

Sir:

Before examination of the above-referenced application, please amend the application as follows:

IN THE CLAIMS:

Please delete claims 1, 2 and 4 and rewrite as claims 1, 2 and 3 as follows:

1. An aromatic polyamide resin composition consisting of an aromatic polyamide resin having a melting point of at least 290 C, an inorganic filler, and an elastomeric impact modifier wherein the composition has a ratio of the weight M of said inorganic filler to the weight T of said impact modifier of $2.0 \leq M/T \leq 6.5$.

2. An aromatic polyamide resin composition of claim 1 wherein the composition has a melt viscosity, measured with a capillary rheometer at a shear rate of 1000/sec and a process temperature 20-30 C higher than the melting point of said aromatic polyamide resin, of 350 Pa sec or less.

3. The aromatic resin composition of Claim 1 wherein the elastomeric impact modifier is ethylene/propylene/diene monomer copolymer rubber.

DRAFT